

Innovative ECA for ribbon bonding on crystalline cells

用于粘接焊带和电池片的新型导电胶

Advantages

- ✓ Low temp. curing
- ✓ Fast curing
- ✓ Lead-free
- ✓ 2-part product
- ✓ No bus bars needed
- ✓ Screen printing

Benefits

- low stress
- cycle time = soldering
- RoHS compliant
- No frozen logistics
- Cost saving potential
- Flexible cell designs

特点


- ✓ 低温固化
- ✓ 快速固化
- ✓ 无铅
- ✓ 双组份
- ✓ 电池片无需主栅
- ✓ 可丝网印刷

利益

- 无热应力
- 工序时间等同焊接
- 符合RoHS标准
- 不需要低温运输
- 降低成本
- 可用于柔性电池

Performance

+2% power compared to soldering




* LCR (light capturing ribbon) supplied by Ulbrich of Austria GmbH / Encapsulant supplied by Isovoltaic

性能

粘接方案使电池效率提升2%

Reliability

< 1% Pmpp loss after TC200 + HF10 and 1000h DH



可靠性

经过TC200+HF10和1000小时DH后，PmPP损失小于1%

Stringing-Process

- | | |
|--|--|
| <ul style="list-style-type: none"> • Curing temperature of 180°C • short cycle times (2,5sec) • 1400 cycles / hour possible • Mono- / polycrystalline cells w/o busbar • long adhesive pot life | <ul style="list-style-type: none"> • 固化温度为180°C • 节拍短(2,5秒) • 生产节拍1400次 / 小时 • 可用于单/多晶，有/无主栅电池 • 生产保质期长 |
|--|--|

串接工艺